



## NON FERROUS TYPICAL SCREEN ANALYSIS

US SIEVE	AFS 85	AFS 100	AFS 115	AFS 130	AFS 145
30	0	0	0	0	0
40	0	0	0	0	0
50	1	1	0	0	0
70	26	18	13	11	1
100	40	35	26	17	9
140	20	24	29	29	39
200	7	10	15	20	24
270	4	7	10	13	15
PAN	2	5	7	10	12
AFS No.	85.2	100.9	115.7	130.4	145.4

